


AXIOTHERM® PCMs are designed to absorb and release large quantities of thermal energy at constant temperatures. Over 30 organic (ATP) and inorganic (ATS) high-performance PCM in a temperature range between -40 °C to 140 ° are available in special macro-encapsulated form with an optimized surface-to-mass ratio for faster energy exchange and improved performance in practical applications. Standardised solutions such as our HeatSel®s and HeatPlates are available for water and air-based applications and can be adapted to your specific requirements.

Key features of the AXIOTHERM® PCM are:

- High heat storage capacities
- Consistent, repeatable performance over thousands of thermal cycles
- Simple and safe handling
- Also based on renewable raw materials, nontoxic and biodegradable

### Typical Values

Material macroencapsulation		none
nucleation temperature	°C	none
Melting temperature	°C	4 to 7
Congeeing temperature	°C	3 to 5
Heat storage capacity*		
temperature range of -2°C – 13°C	kJ/kg	240
Specific heat capacity	kJ/kg*K	2
Density (liquid at 20°C)	kg/l	0,75
Heat conductivity	W/(m*K)	0,2
Volume expansion	%	<10
Max. operating temperature	°C	65
Flash point	°C	115
Corrosion		No corrosive effect on metals
cycling category		D (≥500 cycles)



### Axiotherm GmbH

Bahnhofstraße 31  
D-07607 Eisenberg/Thüringen  
Phone: +49 (0) 36691 53 118  
Fax: +49 (0) 36691 53 120  
E-Mail: [Mailbox@axiotherm.de](mailto:Mailbox@axiotherm.de)  
Web: [www.axiotherm.de](http://www.axiotherm.de)

The product information given is a non-binding planning aid, subject to technical changes without notice.  
Version: 30.10.2020

\*Measured with 3-Layer-Calorimeter



## RAL-Charts PCM t-t 5.5

T-Intervall/ T-Intervall [°C]		Stored heat/ gespeicherte Wärme [J/g]	Stored heat/ gespeicherte Wärme [J/ml]
-2	-2,5 - -1,5	2,6	1,9
-1	-1,5 - -0,5	2,3	1,8
0	-0,5 - 0,5	3,0	2,3
1	0,5 - 1,5	2,7	2,1
2	1,5 - 2,5	4,1	3,1
3	2,5 - 3,5	4,6	3,4
4	3,5 - 4,5	8,6	6,5
5	4,5 - 5,5	42,0	31,5
6	5,5 - 6,5	146,5	109,9
7	6,5 - 7,5	9,1	6,8
8	7,5 - 8,5	4,1	3,1
9	8,5 - 9,5	2,5	1,9
10	9,5 - 10,5	1,6	1,2
11	10,5 - 11,5	2,5	1,9
12	11,5 - 12,5	1,6	1,2
13	12,5 - 13,5	2,7	2,0
Dichte bei 20 °C [g/ml]		0,75	Density at 20 °C [g/ml] 0,75

T-Intervall/ T-Intervall [°C]		Stored heat/ gespeicherte Wärme [J/g]	Stored heat/ gespeicherte Wärme [J/ml]
-2	-2,5 - -1,5	2,4	1,8
-1	-1,5 - -0,5	2,1	1,5
0	-0,5 - 0,5	2,6	2,0
1	0,5 - 1,5	3,2	2,4
2	1,5 - 2,5	3,8	2,9
3	2,5 - 3,5	4,9	3,7
4	3,5 - 4,5	11,9	8,9
5	4,5 - 5,5	53,4	40,1
6	5,5 - 6,5	139,5	104,6
7	6,5 - 7,5	2,0	1,5
8	7,5 - 8,5	2,8	2,1
9	8,5 - 9,5	3,0	2,2
10	9,5 - 10,5	2,4	1,8
11	10,5 - 11,5	2,5	1,9
12	11,5 - 12,5	2,6	1,9
13	12,5 - 13,5	2,3	1,7
Dichte bei 20 °C [g/ml]		0,75	Density at 20 °C [g/ml] 0,75

PCM t-t 5.5



melting				
	Onset (°C)	Peak (°C)	Offset (°C)	Enthalpie (J/g)
	4,6	5,6	6,4	241

crystallization				
	Onset (°C)	Peak (°C)	Offset (°C)	Enthalpie (J/g)
	5,6	5,6	4,6	241

\*Measured with 3-Layer-Calorimeter